



KR9355

LDPE/LLDPE MIX

COMPOSITION: Low density polyethylene/Linear low-density polyethylene mix
COLOR: Black
APPLICATION: Pipe/Sheet extrusion

PROPERTY	UNIT	VALUE	TEST METHOD
MFI	g/10 min (190C /2,16kg)	0,850	ISO1133-1/B
MFI	g/10 min (190C/5kg)	2,97	ISO1133-1/B
MVR	cm ³ /10min	53,7	ISO1133-1/B
Density	g/dm ³	935	ISO1183
Ash	%	<3%	ISO3451
Tensile strength	MPa	13,1	ISO527-2/1B/50
Elongation at break	%	210	ISO527-2/1B/50
Tensile modulus	MPa	256	ISO527-2/1B/1
Impact strength	kJ/m ²	75,9	ISO179-1/1eC
Filtration	Micron	90, 150	
Smell	Typical smell of recycled plastic material.		
Packing	Approximately 1200 kg / jumbo bag		

